

**PRODUCT SPECIFICATION
LIGHT NEUTRAL SLACK WAX-1420**

Property	Test Unit	Guarantee	Limit	Test Method	
				ASTM	IP
Gravity at 15.6 °C	API	35-45			D 287
Color, 10 % Dilute	ASTM	1.0	Max		D 1500
Flash Point	°C	200	Min		D 92
Melting Point	°C	45	Min		D 127
Oil Content	wt %	17	Max		D 721
Viscosity at 100 °C	cSt	2.5-4.5			D 445
Sulfur	wt %	0.5	Max		D 129
Conradson Carbon Residue	wt %	0.08	Max		D 189

(*) This product is produced only in İzmir Refinery.