

**PRODUCT SPECIFICATION
SPINDLE EXTRACT-1310**

Property	Test Unit	Guarantee	Limit	Test Method	
				ASTM	IP
Gravity at 15.6 °C	API	8-11		D 287	
Color, 10 % Dilute	ASTM	5.0	Max	D 1500	
Flash Point	°C	180	Min	D 92	
Pour Point	°C	1.1	Max	D 97	
Sulfur	wt %	6.5	Max	D 129	
Viscosity at 100 °C	SSU	35-60		D 445	
Aniline Point	°C	35	Max	D 611	
Water	wt %	0.1	Max	D 95	
Ash	wt %	0.01	Max	D 482	

(*) This product is produced only in İzmir Refinery.